1 2 -11- 2003

19

10/510396 DT04 Rec'd PCT/PTO 0 5 OCT 2004

CLAIMS

1. A syntactic polyolefin composition for pipe coating, c h a r a c t e r i s e d in that the composition comprises a β -nucleated propylene polymer comprising 0.0001-2.0 weight% of a β -nucleating agent and microspheres, said composition having a melt flow rate (MFR₂; ISO 1133, condition D) at 230°C/2.16kg in the range of 0.05-30 g/10 min and in that the composition has an elongation at break of at least 3%.

5

10

15

30

35

- 2. A syntactic polyolefin composition according to claim 1, c h a r a c t e r i s e d in that said composition has a melt flow rate (MFR₂; ISO 1133, condition D) at $230^{\circ}\text{C}/2.16\text{kg}$ in the range of 0.5-10 g/10 min and preferably in the range of 1.0-5 g/10 min.
- 3. A syntactic polyolefin composition according to claim 1 or 2, characterised in that said composition has an elongation at break of >5% and preferably >10%.
- 4. A syntactic polyolefin composition according to any one of claims 1 to 3, c h a r a c t e r i s e d in that the β -nucleated propylene polymer is a (co)polymer which comprises at least 90.0 weight% of propylene and up to 10.0 weight% of α -olefins with 2 or 4 to 18 carbon atoms, and that the propylene polymer has a melt flow rate of 0.1-8 g/10 min at 230°C/2.16 kg.
 - 5. A syntactic polyolefin composition according to any one of claims 1 to 4, c h a r a c t e r i s e d in that the composition further comprises a polyolefin homopolymer having a melt flow rate of 100-1500 g/10 min at 230°C/2.16 kg.
 - 6. A syntactic polyolefin composition according to any one of claims 1 to 5, characterised in that the amount of polyolefin is 0-20 weight%, preferably 15-20 weight%.
 - 7. A syntactic polyolefin composition according to any one of claims 1 to 6, character is ed in

BEST AVAILABLE COPY

that the tensile modulus of the composition is at least 1500 MPa determined according to ISO 527.

8. A syntactic polyolefin composition according to any one of claims 1 to 7, character is ed in that the compression strength at 20 MPa/80° determined according to ASTM D695, is > 10 MPa, preferably >15 MPa.

5

10

20

30

35

- 9. A syntactic polyolefin composition according to any one of claims 1 to 8, c h a r a c t e r i s e d in that the K-value of the composition is less than 0.190 $W/m^{\circ}K$.
- 10. A syntactic polyolefin composition according to any one of claims 1 to 9, character is ed in that the density of the composition is 500-850 kg/m3.
- 11. A syntactic polyolefin composition according to
 15 any of claims 1 to 10, c h a r a c t e r i s e d in
 that said microspheres are made of glass, ceramics, epoxy
 resin, phenolic resin or urea-formaldehyde resin.
 - 12. A syntactic polyolefin composition according to any one of claims 1 to 11, character is ed in that said microspheres are untreated microspheres.
 - 13. A syntactic polyolefin composition according to any one of claims 1 to 12, c h a r a c t e r i s e d in that said microspheres have an outer diameter of 1-500 μm , preferably 5-200 μm .
- 25 14. A syntactic polyolefin composition according to any one of claims 1 to 13, characterised in that said microspheres are hollow.
 - 15. A syntactic polyolefin composition according to any one of claims 1 to 14, c h a r a c t e r i s e d in that said microspheres are present in an amount of 10-50 weight%, preferably 20-30 weight% of the composition.
 - 16. A method for the preparation of a syntactic polyolefin composition for pipe coating according to any one of claims 1-15, c h a r a c t e r i s e d in that microspheres are evenly distributed by melt mixing in a composition comprising a β -nucleated propylene polymer and microspheres, said composition having a melt flow

BEST AVAILABLE COPY

21

rate at 230°C/2.16kg in the range 0.05-30 g/10min and in that the composition has an elongation at break of at least 3%.

- 17. A method according to claim 16, charac-5 terised in that said microspheres are added to the molten polymer.
 - 18. A method according to claim 16 or 17, c h a r a c t e r i s e d in that the composition is compounded/homogenised and extruded as a coating on an off-shore pipe in one continuous step.
 - 19. A method according to claim 16 or 17, c h a r a c t e r i s e d in that the composition is pelletized in a first step and in a subsequent step extruded as a coating on an off-shore pipe.

10

20. An off-shore pipe coated with a syntactic polyolefin composition, c h a r a c t e r i s e d in that the pipe is coated with a composition according to any one of claims 1-15.